



# DUOFLEX



POLYURETHANE  
MATT



165°C



PEEL : COLD



Flock Blade 60°



460 µm



20 Sec.

## SPECIFICATIONS

### APPLICATION

1. Cut the material in reverse with a flex or flock blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 165°C & Protect the polyester carrier with silicone paper 20 sec - low pressure
4. Peel the carrier off when cold

THICKNESS:  Polyurethane matt 460 microns

CARRIER: Non-adhesive clear polyester



### APPLIES ON

Cotton • Polyester • Acrylic & Similar Fibres

### CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

#### WASH

- Max 40°C
- Preferably inside out
- Do not bleach
- Tumble-dry *tests being processed*
- Dry-cleaning *tests being processed*

#### STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

 **Chemica**  
Heat transfers for textiles

NOTE: For best results, it is recommended to TEST prior to starting standard production