



QUICKFLEX



PU	165°C	PEEL : HOT	Flex Blade 45° Medium Pressure	80 µm	5 SEC
----	-------	------------	-----------------------------------	-------	-------

SPECIFICATIONS

THICKNESS: Polyurethane 80 microns

CARRIER: Adhesive & Transparent polyester

CERTIFICATES: Oeko-Tex Label Standard 100 Class 1
 Oeko-Tex Label Standard 100 Class 2 : 3502

APPLICATION

1. Cut the material in reverse with a Flex blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 165 ° C & Protect the polyester carrier with silicone paper
5 sec - medium pressure
4. Peel the carrier off when hot



APPLIES ON

Cotton • Polyester • Acrylic & Similar Fibres

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 60° C
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning unapproved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position



NOTE: For best results, it is recommended to TEST prior to starting standard production