



REFLEX 427



POLYURETHANE



160°C



PEEL : COLD



Flex Blade 45°
Medium Pressure



150 - 160 µm



20 Sec

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flex blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 160° C & Protect the polyester carrier with silicone paper 20 sec - medium pressure
4. Peel the carrier off when cold

THICKNESS:  Reflective polyurethane material
150 - 160 microns

CARRIER: Self-adhesive and clear polyester.



APPLIES ON

Cotton ● Polyester ● Acrylic & Similar Fibres

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 60° C
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

Chemica
Heat transfers for textiles

NOTE: For best results, it is recommended to TEST prior to starting standard production